

10/500084
DT04 Rec'd PCT/PTO 24 JUN 2004

AMENDMENTS TO THE CLAIMS

This listing of claims will replace all prior versions, and listings, of claims in the application:

Listing of Claims

Claims 1-9. (Cancelled)

Claim 10 (new): A resin composition for reflector plates comprising 30 to 95% by weight of a semi-aromatic polyamide having the ratio of aromatic monomers to all the monomer components being at least 20% by mole, and 5 to 70% by weight of potassium titanate fiber or wollastonite, or both.

Claim 11 (new): The resin composition for reflector plates according to claim 10, wherein

said semi-aromatic polyamide comprises a semi-aromatic polyamide containing, as monomer components, an aromatic dicarboxylic acid and an aliphatic alkylenediamine.

Claim 12 (new): The resin composition for reflector plates according to claim 11, wherein

said semi-aromatic polyamide comprises a semi-aromatic polyamide further containing, as a monomer component, an aliphatic dicarboxylic acid.

Claim 13 (new): A resin composition for reflector plates used for an ultraviolet-ray generating source, comprising a thermoplastic resin and at least one inorganic compound selected from the group consisting of fibrous and flaky inorganic compounds capable of reflecting ultraviolet rays as well as visible light.

Claim 14 (new): The resin composition for reflector plates according to claim 13, wherein

the fibrous and flaky inorganic compound capable of reflecting ultraviolet rays as well as visible light is a compound containing potassium titanate.

Claim 15 (new): The resin composition for reflector plates according to claim 14, wherein

the compound containing potassium titanate comprises at least one selected from the group consisting of potassium titanate fiber, flaky lithium potassium titanate, and flaky potassium magnesium titanate.

Claim 16 (new): The resin composition for reflector plates according to claim 13, wherein

the thermoplastic resin comprises at least one thermoplastic resin that absorbs little visible light or transparent thermoplastic resins, or both.

Claim 17 (new): The resin composition for reflector plates according to claim 16, wherein

the thermoplastic resin that absorbs little visible light or the transparent thermoplastic resin, or both, comprises at least one selected from the group consisting of semi-aromatic polyamides, aliphatic polyamides, liquid crystal polymers, syndiotactic polystyrene, polybutylene terephthalate, polyethylene terephthalate, polyethylene naphthalate, polymethylpentene, and polyacetal.

Claim 18 (new): The resin composition for reflector plates according to claim 13, comprising 30 to 95% by weight of a thermoplastic resin and 5 to 70% by weight of an inorganic compound capable of reflecting ultraviolet rays as well as visible light.

Claim 19 (new): The resin composition for reflector plates according to claim 14, wherein

the thermoplastic resin comprises at least one thermoplastic resin that absorbs little visible light or transparent thermoplastic resins, or both.

Claim 20 (new): The resin composition for reflector plates according to claim 15, wherein

the thermoplastic resin comprises at least one thermoplastic resin that absorbs little visible light or transparent thermoplastic resins, or both.

Claim 21 (new): The resin composition for reflector plates according to claim 14, comprising 30 to 95% by weight of a thermoplastic resin and 5 to 70% by weight of an inorganic compound capable of reflecting ultraviolet rays as well as visible light.

Claim 22 (new): The resin composition for reflector plates according to claim 15, comprising 30 to 95% by weight of a thermoplastic resin and 5 to 70% by weight of an inorganic compound capable of reflecting ultraviolet rays as well as visible light.

Claim 23 (new): The resin composition for reflector plates according to claim 16, comprising 30 to 95% by weight of a thermoplastic resin and 5 to 70% by weight of an inorganic compound capable of reflecting ultraviolet rays as well as visible light.

Claim 24 (new): The resin composition for reflector plates according to claim 17, comprising 30 to 95% by weight of a thermoplastic resin and 5 to 70% by weight of an inorganic compound capable of reflecting ultraviolet rays as well as visible light.

Claim 25 (new): The resin composition for reflector plates according to claim 19, wherein

the thermoplastic resin that absorbs little visible light or the transparent thermoplastic resin comprises at least one selected from the group consisting of semi-aromatic polyamides, aliphatic polyamides, liquid crystal polymers, syndiotactic polystyrene, polybutylene terephthalate, polyethylene terephthalate, polyethylene naphthalate, polymethylpentene, and polyacetal.

Claim 26 (new): The resin composition for reflector plates according to claim 20, wherein

the thermoplastic resin that absorbs little visible light or the transparent thermoplastic resin comprises at least one selected from the group consisting of semi-aromatic polyamides, aliphatic polyamides, liquid crystal polymers, syndiotactic polystyrene, polybutylene terephthalate, polyethylene terephthalate, polyethylene naphthalate, polymethylpentene, and polyacetal.